

VPOJNI KARTON

Vpojni karton je sestavljen iz beljenih celuloznih sulfatnih listavcev in iglavcev. Karton je zaradi velike vpojnosti sestavljen iz surovih nemletih vlaken.

Vpojni karton se uporablja pri izvedbi laboratorijskih testov vodovpojnosti papirja Cobb, saj ustreza zahtevam standarda ISO 535, pri izdelavi laboratorijskih papirjev na konvencionalnih oblikovalnikih papirjev in ustreza standardu ISO 5269-1.

| Lastnost | Standard | |
|---------------------------------|-----------------|----------|
| Gramatura [g/m ²] | SIST EN ISO 536 | 250 ± 25 |
| Vpojnost Klemm [mm] | ISO 8787 | 70 ± 20 |
| Navzem vode [g/m ²] | ISO 5269-1 | 450 ± 50 |

Ostale karakteristike

Dimenzije formata:

A3, po dogovoru. Najbolj uporabljena (prodajna) dimenzija je 42 x 62 cm.

Dimenzije zvitkov:

Maksimalna širina zvitkov je 62 cm, dolžina po dogovoru.

Dobava:

Minimalna količina papirja in kartona je od 10 do več 10 000 pol oziroma od nekaj kg do več 1000 kg.

Manjšo količino papirja in kartona imamo vedno na zalogi.

Rok dobave po dogovoru.

BLOTTER BOARD

Blotter board is made from unmilled fibers of bleached kraft pulp.

Blotter board is used for carrying out laboratory test for water absorption – COBB test, and corresponds to the requirements of ISO 535 and in laboratory, for conventional sheet formers, according to ISO 5269–1.

| Properties | Standard | |
|----------------------------------|------------|----------|
| Grammage [g/m ²] | ISO 536 | 250 ± 25 |
| Klemm absorbancy [mm] | ISO 8787 | 70 ± 20 |
| Water uptake [g/m ²] | ISO 5269–1 | 450 ± 50 |

Other characteristics:

Sheet dimensions: A3 or by agreement, the most used dimension is 42 x 60 cm

Reel dimensions: maximum reel is 62 cm, length by agreement

Delivery:

Quantity of board is from 10 to 10 000 sheets or from 1 kg to more 1000 kg.

Minimum quantity of board is always on stock.

Delivery time is by agreement with customer.