

ICP PERMANENT PAPER AND BOARD (PP1)

ICP Permanent paper and board PP1 is made of bleached kraft pulp, with the addition of calcium carbonate fillers and without optical brightening agent.

Product is suitable for writing, drawing and printing for permanence material, for the protection of material in archives, museums, libraries, galleries for long life storage and for conservation and restoration.

Paper and board correspond to requirements, according to ISO 9706 (Information and documentation – Paper for documents – Requirements for permanence) and ISO 11108 (Information and documentation – Archival paper – Requirements for permanence and durability).

Properties	Standard					
Grammage [g/m ²]*	ISO 536	50 ± 2	80 ± 3	110 ± 3	140 ± 5	250 ± 8
Ash content on ignition at 525°C [%]	ISO 1762	Min 3				
pH value of aqueous extract	ISO 6588	8 – 9				

*possible of producing intermediate grammage 50 – 300 g/m²

Other characteristics:

Sheet dimensions: A3, A4 or by agreement, maximum width is 62 cm

Reel dimensions: maximum width is 62 cm, length by agreement

Delivery:

Quantity of paper and board is from 10 to 10 000 sheets or from 1 kg to more 1000 kg.

Minimum quantity of paper and board is always on stock.

Delivery time is by agreement with customer.

Extra offer:

For storage of thicker documents or books, paper and board can be creased with one or more parallels creases.

ICP PERMANENT PAPER AND BOARD (PP2)

ICP Permanent paper and board PP2 is improved product of ICP Permanent paper and board PP1. It is made of mixture of cotton and bleached kraft pulp, with the addition of calcium carbonate fillers and without optical brightening agent.

ICP Permanent paper and board PP2 is used for writing, drawing and printing materials for permanence material, for the protection of material in archives, museums, libraries, galleries for long life storage and for conservation and restoration.

Complies with ISO 9706 (Information and documentation- Paper for documents – Requirements for permanence) and ISO 11108 (Information and documentation – Archival paper – Requirements for permanence and durability), as well as the minimum requirements for the protection of archival and photographic materials in ISO 18902 (Imaging materials – Processed imaging materials- Albums, framing and storage materials).

Property	Standard					
Grammage [g/m ²]	ISO 536	50 ± 2	80 ± 3	110 ± 3	150 ± 5	250 ± 8
Ash content on ignition 525°C [%]	ISO 1762	Min 3				
pH value of aqueous extract	ISO 6588	8 – 9				

Other characteristics:

Sheet dimensions: A3, A4 or by agreement, maximum width is 62 cm

Reel dimensions: maximum reel is 62 cm, length by agreement

Delivery:

Quantity of paper and board is from 10 to 10 000 sheets or from 1 kg to more 1000 kg.

Minimum quantity of paper and board is always on stock.

Delivery time is by agreement with customer.

Extra offer:

For storage of thicker documents or books, paper and board can be creased with one or more parallels creases.

ICP PERMANET PAPER AND BOARD FOR PHOTOGRAPHIC MATERIALS PRESERVATION (PP3)

ICP permanent paper for photographic materials preservation (PP3) is made from cotton and minimum content of bleached kraft pulp, with the addition of calcium carbonate fillers and without optical brightening agent.

For permanent paper for photographic materials preservation we received the certificate for PAT test (*Photographic Activity Test*) according to ISO 18916 (Imaging materials – Processed imaging materials – Photographic activity test for enclosure materials), issued by the National Archives of Australia, The Paper Testing Laboratory. PAT test confirms, that product is suitable for the protection of archival and photographic materials according to ISO 18902 (Imaging materials – Processed imaging materials- Albums, framing and storage materials).

ICP Permanent paper for photographic materials preservation corresponds also to requirements, according to ISO 9706 (Information and documentation- Paper for documents – Requirements for permanence) and ISO 11108 (Information and documentation – Archival paper– Requirements for permanence and durability).

Properties	Standard		
Grammage [g/m ²]	ISO 536	50 ± 2	120 ± 4
Ash content on ignition at 525°C [%]	ISO 1762	Min 3	
pH value of aqueous extract	ISO 6588	8 – 9	

Other characteristics:

Sheet dimensions: A3, A4 or by agreement, maximum width is 62 cm

Reel dimensions: maximum width is 62 cm, length by agreement

Delivery:

Quantity of paper and board is from 10 to 10 000 sheets or from 1 kg to more 1000 kg. Delivery time is by agreement with customer.

Extra offer:

For storage of thicker documents or books, paper and board can be creased with one or more parallels crease.